












# PORCELLANATO

IMPASTO COLORATO

DPOT00 P-ONE TOZZ. STEEL **510/PZ**  
1,5x1,5 0,6"x0,6"

DTCL00 LISTELLO STEEL  
1,5x59,5 0,6"x23,5"

**535/PZ**

| <b>Dati tecnici secondo norme:</b><br><b>Technical data conform to:</b><br><b>Caractéristiques techniques d'après normes:</b><br><b>Technische Daten nach den Normen:</b> |  |                                   |   | <b>EN14411: 2003</b><br><b>Appendice: G</b><br><b>Gruppo B<sub>1</sub> GL</b>       |  |                                   |   |
|---|--|-----------------------------------|---|---|--|-----------------------------------|---|
|   | Caratteristiche tecniche<br>Technical data<br>Caractéristiques techniques<br>Technische Daten  | Norme<br>Normes<br>Normes<br>Norm | Valori<br>Value<br>Valeur<br>Wert                     |   | Caratteristiche tecniche<br>Technical data<br>Caractéristiques techniques<br>Technische Daten            | Norme<br>Normes<br>Normes<br>Norm | Valori<br>Value<br>Valeur<br>Wert                               |
|    | Resistenza all'abrasione<br>Abrasion resistance<br>Resistance à l'abrasion<br>Abrasionswiderstandigkeit  | ISO 10545-7                       | <b>PEI V</b>  |    | Resistenza al gelo<br>Resistance to frost<br>Resistance au gel<br>Frostbeständigkeit                     | ISO 10545-12                      | <b>Non gelive<br/>Frost proof<br/>Ingefälf<br/>Froststicher</b> |
|   | Assorbimento d'acqua<br>Water absorption<br>Absorption d'eau<br>Wasseraufnahme   | ISO 10545-3                       | ≥ <b>0,5%</b>   |   | Scivolamento B.C.R.A.<br>Slipperiness B.C.R.A.<br>Degré de glissement B.C.R.A.<br>Rutschhemmung B.C.R.A. | TORTUS                            | <b>WET &gt; 0,33<br/>DRY &gt; 0,41</b>                          |
|    | Resistenza alla flessione<br>Breaking modulus<br>Resistance à la flexion<br>Biegefestigkeit  | ISO 10545-4                       | ≥ <b>40±50 N/mm²</b>                                  |  | Scivolosità<br>Slipperiness<br>Degré de glissement<br>Rutschhemmung                                      | ASTM C1028                        | ≤ <b>0,60</b>   |
|    | Durezza Mohs<br>Mohs hardness<br>Dureté Mohs<br>Haerte Mohs  | EN101                             | <b>7</b>  |  | Scivolosità<br>Slipperiness<br>Degré de glissement<br>Rutschhemmung                                      | DIN 51130                         | <b>R10</b>  |
|    | Resistenza all'attacco acido e basico<br>Glaze resistance to acid and alkaline attack<br>Resistance aux acides et aux bases<br>Säure- und laugenfestigkeit | ISO 10545-13                      | <b>Resiste<br/>Resists<br/>Resiste<br/>Bestanding</b> |  | Resistenza allo scivolamento<br>Slip resistance<br>Resistance au glissement<br>Rutschhemmung             | DIN 51097                         | <b>A</b>  |
|    | Resistenza alle macchie<br>Stain resistance<br>Resistance aux taches<br>Fleckenfestigkeit  | ISO 10545-14                      | <b>Totale<br/>Complete<br/>Totale<br/>Absolut</b>     |   |  |                                   |   |

